

ISIL İLETKENLİK DENEY SONUÇLARI *results of thermal conductivity test*

Expanded Polistren Köpük (EPS) KAR-PANEL (16-20-26-30) kg/m³

Expanded Polystyrene Foam (EPS)KAR-PANEL (16-20-26-30)kg/m³

Normal Dansite <i>Normal Density</i>	Isı İletkenlik Katsayısı [W.m ⁻¹ .K ⁻¹] <i>Thermal Conductivity Factor</i>	Termal Direnç Değeri [m ² .K/W] <i>Thermal Resistance Value</i>	Atıf Yapılan Standart <i>Referenced Standard</i>	Test Standartı <i>Test Standard</i>
16 kg/m ³	0,036912	1,397343	EN 13163:2008	EN 12667/EN 12939
20 kg/m ³	0,034907	1,423217	EN 13163:2008	EN 12667/EN 12939
26 kg/m ³	0,03432	1,44961	EN 13163:2008	EN 12667/EN 12939
30 kg/m ³	0,032669	1,55022	EN 13163:2008	EN 12667/EN 12939

